

LLOYD MINE

AVERAGE MINE ANALYSIS ON OUTPUT FOR YEAR - 1918.

GRADE	IRON	PHOS.	SILICA
Lloyd Bessemer,	59.68	.050	6.15
Lloyd,	59.02	.084	6.84
Lloyddale,	59.55	.141	5.61
North Lake Silica,	52.17	.068	16.93

AVERAGE ANALYSIS ON STRAIGHT CARGOES FOR YEAR - 1918.

GRADE	Mine		Lake Erie	
	IRON	PHOS.	IRON	MOIST.
Lloyd Bessemer,	All Mixed			
Lloyd,	59.06	.086	59.00	10.54
Lloyddale,	All Mixed			
North Lake Silica,	51.41	.062	53.61	10.33

ORE STATEMENT - DECEMBER 31ST, 1918.

	LLOYD BESSEMER	LLOYD	NORTH LAKE SILICA	LLOYDDALE	TOTAL	TOTAL LAST YEAR
On hand Jan. 1st, 1918,	916	31,006	15,293	23,960	71,175	60,660
Output for Year,	1,763	146,152	33,786	59,551	241,252	202,847
Total,	2,679	177,158	49,079	83,511	312,427	263,507
Shipments,	2,679	155,166	45,322	60,087	263,254	192,332
Balance on Hand,	0	21,992	3,757	23,424	49,173	71,175
Increase in output - 19%					38,405	
Decrease in ore on hand,					22,002	

2-8 Hour Shifts - 1917 & 1918.

LLOYD MINE.

LLOYD MINE

SHIPMENTS FOR YEAR -- 1918.

GRADE	POCKET	STOCKPILE	TOTAL	TOTAL LAST YEAR	
Lloyd Bessemer,	2,545	134	2,679	26,108	
Lloyd,	115,562	39,604	155,166	117,632	
North Lake Silica,	20,744	24,578	45,322	36,085	
Lloyddale,	38,668	21,419	60,087	12,507	
Total,	177,519	85,735	263,254	192,332	
Total last Year,	131,147	61,185	192,332		
Increase - 37%			70,922		

LLOYD MINE.